

# B

## BRIGHT-IN

### MANUFACTURER

#### Barinsa, S.A.

Camino Frailes, s/n  
 43570 Santa Bárbara (Tarragona)  
 T + (34) 977 718 000  
 F + (34) 977 718 261

[info@barinsa.es](mailto:info@barinsa.es)/[www.barinsa.es](http://www.barinsa.es)

### CHARACTERISTICS OF THE BASE BOARD

#### 1. DIMENSIONAL TOLERANCES CHARACTERISTIC

CHARACTERISTIC	VALUE	STANDARD
Formato	2850x1220x18	
Lenght/width (mm)	+/- 5	EN 324-1
Thikness (mm)	+/- 0,3	EN 324-1
Squad (mm/m)	+/- 2	EN 324-2
Straightness (mm/m)	+/- 1,5	EN 324-2

#### 2. PHYSICAL-MECHANICAL PROPERTIES CHARACTERISTIC

CHARACTERISTIC	VALUE	STANDARD	VOPTIMAL VALUE
Cold liquids resistance 6h (value)	6 hours: 5 except etanol 96% with 4, 1h: 5	UNE-EN12720:09+A1:2014	5
Adhesion of the coating 2mm (value)	1	EN ISO 2409:2013	
Superficial skewback	1,53 (0,1)	EN 311:2002	
Crack resistance (value)	5		
cold heat cycle (cold check)	without variations		
Cold fastness (degree)	5 (without variations)		
Dry heat 180°C (value)	5	UNE-EN 12722:09+A1:2014	5
Humid heat 100°C (value)	5	UNE-EN 12721:09+A1:2014	5
Scratch resistance/method A (N)	>20	UNE-EN 15186:2012 (método A)	20
Wear resistance	190	UNE EN 13329	
Water vapor resistance (value)	5	UNE-EN 14323:2017	5
Impact resistance to falling ball		UNE-EN 14323:2017	
Heigh mm	900		>10
Footprint diameter (mm)	<10		