



MANUFACTURER

BARINSA, S.L.
 Camino Fraules, s/n
 43570 Santa Bárbara (Tarragona). ES
 T + (34) 977 718 000
 comercialbarinsa.es | www.barinsa.es

PRODUCT

Delta Vintage Floor: high-resistance finish HOT COATING by kleiberit, based on Agepan OSB3 with male / female glued installation system and dimensions 2100mm x 300mm and 1200mm x 600mm, in both cases with a thickness of 12mm. Board of the following characteristics.

Thickness	12mm±0.8mm (EN 324-1)
Density	600±40 kg/m ³ (EN 323)
Moisture content	9±3 % (EN 322)
Swelling in thickness after immersion (24)	≤12% (EN 317)
Content in formaldeido	≤5 mg CH ₂ OH/100g dry board (EN 120)
Reaction to fire	B2 (DIN 4102 T1)

*information provided by the manufacturer under his responsibility

ESSAYS PERFORMED⁽¹⁾

TRIAL NORM

RESULT

Abrasion resistance (cycle)	UNE-EN 13329:2016 (anexed E)	6000 (AC5)
Impact resistance	UNE EN 14527:2016	
- Large diameter ball (mm)		1300
- Small diameter ball (N)	UNE-EN 13329:2016 (anexed H)	25
Stain resistance (grade)	UNE-EN 13329:2016 (anexed H)	5
Effect of furniture leg	UNE-EN 13329:2016 (EN 438-2 apdo.26)	(trial)
Effect of the chair with wheels	UNE-EN 424:2002	(trial)
Surface start 8n/mm ²)	UNE-EN 425:2002	1.14 N
Slipperiness (kind)	UNE-EN 13329:2016 (anexed D)	1
Average value of Rd	UNE-ENV 12633:03 (CTE DB-SUA)	30



October 2018

The tests described in this file have been carried out in the AIDIMME laboratory (ESG46261590) at the request of the product manufacturer. The results obtained only concern the sample analyzed. These results are included in the reports of the tests nº 220.I.1712.923.ES.01 and nº221.I.1810.723.ES.01.